

LUSEP GP2400H

Injection Molding Grade, PPS+GF40%

Description

General Purpose

Application

Pump Units, Motor Units, etc.

Properties	Test Condition	Test Method	Unit	Typical Value
Physical				
Density		ISO 1183	g/cm ³	1.64
Molding Shrinkage	2mm	ISO 294-4	%	0.1 ~ 0.2
Mechanical				
Tensile Strength		ISO 527		
@ Break	23 °C, 5mm/min		MPa	210
Tensile Elongation		ISO 527		
@ Break	23 °C, 5mm/min		%	< 1.5
Flexural Strength	2mm/min	ISO 178	MPa	275
Flexural Modulus	2mm/min	ISO 178	MPa	12,000
Charpy Impact Strength, 80*10*4mm (Notched)	23 °C	ISO 180/1A	kJ/m ²	10.0
Thermal				
Heat Deflection Temperature (Unannealed)	1.8MPa, Flatwise 0.45MPa	ISO 75	°C °C	>260
Flammability 0.71mm		UL94	class	V-0
Electrical				
Comparative Tracking Index(CTI)	Solution A	UL746	PLC	-
Dielectric Strength, 1mm	23 °C	IEC 60243-1	kV/mm	-

Note) ▪ The property values above are give by Tech Center, LG Chemical Ltd. as a reference only, and are not inteded for specification purposes.

When pigmnets are loaed, there might be slight changes in the properties.

▪ All properties, except melt flow rate are measured on injection molulded specimens and after **48 hours** storage at 23 °C, 50% relative humidty.

Updated : 17-Feb-17

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

LUSEP GP2400H

Injection Molding Grade, PPS+GF40%

Processing Guide (Injection Molding)

Processing Parameters		Unit	Value
Drying Temperature		℃	100 ~ 120
Drying Time		hrs	2 ~ 4
Minimum Moisture Content		%	0.02
Melt Temperature		℃	300 ~ 330
Cylinder Temperature	Rear	℃	300
	Middle	℃	310
	Front	℃	320
Nozzle Temperature		℃	330
Mold Temperature		℃	120 ~ 150
Back Pressure		kg/cm ²	-
Screw Speed		rpm	<100

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Updated : 17-Feb-17

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.