

LUPOY PC2001-20

Injection Molding & Extrusion Grade, PC

Description

FDA compliance¹⁾, Good mold release,
Low viscosity, Bio-compatibility ISO 10993 certified
EtO and steam sterilization at 121°C

Application

Medical Devices
(Syringes, Dialyzers, Connectors) Ver. 23.07

Properties	Test Condition	Test Method	Unit	Typical Value
Physical				
Specific Gravity		ISO 1183	g/cm ³	1.20
Molding Shrinkage		ISO 294-4	mm/mm	0.005~0.007
Melt Flow Rate	300°C/1.2kg	ISO 1133	cm ³ /10min	19
Optical				
Refractive Index, n _D		ISO 489		1.586
Light Transmittance		ASTM D 1003	%	89
Haze		ASTM D 1003	%	<1.5
Mechanical				
Tensile Strength (@ Yield)	50mm/min	ISO 527	MPa	60
Tensile Elongation (@ Break)	50mm/min	ISO 527	%	>100
Flexural Strength	2mm/min	ISO 178	MPa	96
Flexural Modulus	2mm/min	ISO 178	MPa	2,300
Charpy Impact Strength (Notched)	23°C	ISO 179	KJ/m ²	65
Izod Impact Strength (Notched)		ISO 180	KJ/m ²	65
Thermal				
Heat Deflection Temperature (unannealed, Flatwise)	0.45MPa	ISO 75	°C	131
(unannealed, Flatwise)	1.8MPa		°C	121
Vicat Softening Point	5kg, 50°C/h	ISO 306	°C	142

1) When used unmodified for the manufacture of food contact articles LUPOY PC2001-20 Polycarbonate resins comply with the U.S. Food, Drug, and Cosmetic Act and Food Additive Regulations 21 CFR 177.1580 and E.U. Food Contact Regulations

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molulded specimens and after 48 hours storage at 23°C, 50% relative humidity.

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

LUPOY PC2001-20

Injection Molding & Extrusion Grade, PC

Description

FDA compliance¹⁾, Good mold release,
Low viscosity, Bio-compatibility ISO 10993 certified
EtO and steam sterilization at 121°C

Application

Medical Devices
(Syringes, Dialyzers, Connectors)

Ver. 23.07

Electrical

GWT 2.0 mm, 5 second		IEC 60695-2-13	°C	850
Comparative Tracking Index(CTI)	Solution A	IEC 60112	Volts	250
Volume Resistivity	23°C	ASTM D257	Ohm·m	2x10 ¹⁷
Dielectric Strength	23°C	ASTM D149	KV/mm	17
Dielectric Constant (60 Hz)	23°C	ASTM D150		3
Dissipation Factor (60 Hz)	23°C	ASTM D150		0.001
Comparative Tracking Index (2.00 mm)	23°C	IEC 60112	V	250

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection moulded specimens and after 48 hours storage at 23°C, 50% relative humidity.

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	120
Drying Time	hrs	4
Maximum Moisture Content	%	0.02
Melt Temperature	°C	280 ~ 300
Cylinder Temperature	Rear Middle Front	265 ~ 285 270 ~ 290 275 ~ 295
Nozzle Temperature	°C	280 ~ 300
Mold Temperature	°C	80 ~ 120
Back Pressure	kg/cm ²	10 ~ 40
Screw Speed	rpm	40 ~ 70

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.