

EVATANE® 24-03

EVATANE® 24-03 is a random ethylene-vinyl acetate copolymer.

- The high Vinyl Acetate content of EVATANE® 24-03 brings softness, flexibility and polarity. EVATANE® 24-03 delivers high cohesive strength with most fillers and can be used to produce masterbatches or HFFR compounds, and as an additive for bitumen modification.
- EVATANE® 24-03 is also suitable for film (cast or blown) extrusion, and exhibits good adhesion onto PE, PS and polyesters.

Typical Properties

	Test Method	Unit	Typical Value
Vinyl Acetate Content	FTIR (internal method)	%.-wt.	24
Melt Index (190°C/2.16kg)	ISO 1133	g/10min.	3
Melting Point	ISO 11357-3	°C	80
Density	ISO 1183	g/cm ³	0.95
Vicat Softening Temperature (10N) ¹	ISO 306 / ASTM D1525	°C	46
Ring & Ball Temperature	ASTM E28 / NF EN 1238	°C	183
Elongation at Break ¹	ISO 527-2 / ASTM D638	%	900
Tensile Strength at Break ¹	ISO 527-2 / ASTM D638	MPa	27
Hardness Shore A ¹	ISO 868 / ASTM D2240		83

¹: On compression molded samples.

Processing

EVATANE® 24-03 can be processed on most conventional equipment used for thermoplastics. It is recommended to avoid melt temperatures above 230°C and to purge the equipment after a run is completed.

Storage, Handling & Safety

EVATANE® 24-03 should be stored away from heat, humidity and UV-light. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of the EVATANE® 24-03 are available upon request to your SK Functional Polymer representative.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.