

PRODUCER	PLASTIKA KRITIS SA
PRODUCT	<b>KRITILEN BLACK 4403P</b>
<i>Version</i>	150620
DESCRIPTION	Black masterbatch in pellet form.

### PROPERTIES

Carrier Resin	LLDPE (MFI=50gr/10min)
Pigment/Dye	Carbon black
Filler	Yes
Pigment Type	P (particle size 20-25nm)
Other Additives	Processing Stabiliser

### SPECIFICATIONS

	<b>Range</b>	<b>Method</b>
Dispersion at 200mesh (bar)	<= 5.0	OEE-8.2.4-01-08
Total Inorganic Content (%)	50.00 ± 1.50	OEE-8.2.4-01-06
Carbon Black Content (%)	40.00 ± 1.20	OEE-8.2.4-01-06
Volatile Content (%)	<= 0.20	OEE-8.2.4-01-07
Pellet Visual Inspection	Yes	

**PRODUCT**

**KRITILEN BLACK 4403P**

*Version*

*150620*

**PACKAGING & STORAGE**

The product comes in regular pellet form and packed in 25 kg bags (pallets of 1000kg). The bags must be stored indoors for a maximum of 12 months and in a dry environment of approximately 25°C.

**FOOD APPROVAL**

The product is produced using raw materials which, according to our suppliers, comply with the following food contact and/or packaging regulations:

Commission Regulation (EU) No. 10/2011: Yes

EU Directive 94/62/EC: Yes

CONEG Regulation: Yes

**APPLICATIONS**

The product offers a convenient way of incorporating carbon-black in thermoplastics, without dust contamination, insuring good dispersion, which is essential for maximum opacity and UV stabilization. Besides, it is based on a special carbon black, which due to its small particle size (20-25mm) and to its perfect dispersion, offers to the end product the maximum possible UV protection. The recommended addition rate is 5-7% (optimum 6%).

Notice : In order to comply with REG. 10/2011/ EC for food contact, the addition rate of black 4403P should not exceed 6 % in the final article.

The product is recommended for use in the following applications:

Blow Moulding: +

Film/Sheet: +

Injection Moulding: +

Pipe: o

Tapes: +

Thin Films: +

**APPLICATIONS**

*+: Recommended, o: Can be used, x: Not Recommended*

*The above information is based on our knowledge and experience and is given in good faith to be used as recommendations for trials only. As the exact conditions of processing and usage of the finished products are beyond our control, this information is provided without any engagement or warranty from our side. Buyer should verify the suitability of the product and determine the appropriate rate under the actual conditions of applications.*