

PRODUCER	PLASTIKA KRITIS SA
PRODUCT	KRITILEN BLACK 451P
<i>Version</i>	240619
DESCRIPTION	Black masterbatch in pellet form.

PROPERTIES	
Carrier Resin	LLDPE
Pigment/Dye	Carbon black
Pigment Type	P (particle size 20-25nm)
Filler	No
Other Additives	Processing Stabiliser

SPECIFICATIONS		
	Range	Method
Dispersion at 200mesh (bar)	<= 5.0	OEE-8.2.4-01-08
Total Inorganic Content (%)	50.00 ± 1.50	OEE-8.2.4-01-06
Volatile Content (%)	<= 0.20	OEE-8.2.4-01-07
Pellet Visual Inspection	Yes	

PRODUCT

Version

KRITILEN BLACK 451P

240619

PACKAGING & STORAGE

The product comes in regular pellet form and packed in 25 kg bags (pallets of 1000kg). The bags must be stored indoors for a maximum of 12 months and in a dry environment of approximately 25°C.

FOOD APPROVAL

The product is produced using raw materials which, according to our suppliers, comply with the following food contact and/or packaging regulations:

Commission Regulation (EU) No. 10/2011: Yes

EU Directive 94/62/EC: Yes

Resolution AP (89) I: Yes

CONEG Regulation: Yes

APPLICATIONS

The product offers a convenient way of incorporating carbon black into thermoplastics, without dust contamination, insuring good dispersion, which is essential for maximum opacity and UV stabilization. It is based on a special carbon black, which, due to its small particle size (20-25nm) and to its perfect dispersion, offers to the end product the maximum possible UV protection.

Notice : In order to comply with REG. 10/2011/ EC for food contact, the addition rate of BLACK 451P should not exceed 4.85 % in the final article. Detailed declaration is available upon request.

The product is recommended for use in the following applications:

Blow Moulding: o

Film/Sheet: +

Injection Moulding: o

Tapes: o

Thin Films: +

+: Recommended, o: Can be used, x: Not Recommended

The above information is based on our knowledge and experience and is given in good faith to be used as recommendations for trials only. As the exact conditions of processing and usage of the finished products are beyond our control, this information is provided without any engagement or warranty from our side. Buyer should verify the suitability of the product and determine the appropriate rate under the actual conditions of applications.