

PRODUCER	PLASTIKA KRITIS SA
PRODUCT	KRITILEN BLACK A4434P
<i>Version</i>	130224
DESCRIPTION	Black masterbatch in pellet form.

PROPERTIES	
Carrier Resin	LLDPE
Pigment/Dye	Carbon black
Pigment Type	P (particle size 20-25nm)
Filler	No
Main Additives	Polymer Processing Aid Primary Antioxidant Processing Stabiliser

SPECIFICATIONS		
	Range	Method
Dispersion at 325mesh (bar)	<= 10.0	OEE-8.2.4-01-08
Total Inorganic Content (%)	40.00 ± 1.20	OEE-8.2.4-01-06
Volatile Content (%)	<= 0.15	OEE-8.2.4-01-07
Density (gr/cm3)	1.150	ASTM D792
Melt Flow Index (10kg/190C) (gr/10min)	18.0 - 45.0	EN ISO1133
Pellet Visual Inspection	Yes	

PRODUCT

KRITILEN BLACK A4434P

Version

130224

PACKAGING & STORAGE

The product comes in regular pellet form and packed in 25 kg bags (pallets of 1000kg). The bags must be stored indoors for a maximum of 12 months and in a dry environment of approximately 25°C.

FOOD APPROVAL

The product is produced using raw materials which, according to our suppliers, comply with the following food contact and/or packaging regulations:

Commission Regulation (EU) No. 10/2011: Yes

EU Directive 94/62/EC: Yes

Resolution AP (89) I: Yes

CONEG Regulation: Yes

APPLICATIONS

The product offers a convenient way of incorporating carbon-black in thermoplastics, without dust contamination, insuring good dispersion, which is essential for maximum opacity and UV stabilization.

Notice : In order to comply with REG. 10/2011/ EC for food contact, the addition rate of Black A4434P should not exceed 6 % in the final article. Detailed food contact declaration available upon request.

The product is recommended for use in the following applications:

Extrusion: +

PP Fibers: o

Film/Sheet: +

Injection Moulding: +

Pipe: +

Thin Films: +

+: Recommended, o: Can be used, x: Not Recommended

The above information is based on our knowledge and experience and is given in good faith to be used as recommendations for trials only. As the exact conditions of processing and usage of the finished products are beyond our control, this information is provided without any engagement or warranty from our side. Buyer should verify the suitability of the product and determine the appropriate rate under the actual conditions of applications.